

Technical Data Sheet



ScorchProtect™ Clear CLPRG502A

Page: 1 of 2
 Revision: 1 (CVNA)
 Date: 28 June 2023
 Author: NR

ScorchProtect™ CLPRG502A is a Clear perforated self-adhesive vinyl with 50% transparency; and a removable, pressure-sensitive adhesive, featuring a Replacement Liner with Grayliner™ technology. For inside applied one-way vision graphics, print the image design as reverse-read and over-print with white and black ink layers.

For inside applied backlit see-through graphics, print the image design as reverse-read and over-print with a translucent white ink layer. This allows an image to be seen on the outside of a window during the day while allowing viewing through from the inside, and during the hours of darkness allows the image to be backlit so that it can still be seen on the outside. A ghost reverse image of the print can be seen from the inside, although the mind will concentrate on the outside view and not the ghost image.

Typical Properties	
PROPERTY	VALUE
Face film	Clear polymeric calendered PVC
Film thickness	7.1 mils ± 0.4 mils (180µm ± 10 µm)
Hole pattern	50% transparency; 0.08" (2.00mm) diameter holes
Adhesive	Transparent solvent polyacrylate 1.03 oz/yard ² ±0.09 oz/yard ² (35g/m ² ±3g/m ²)
Liner	Unperforated Replacement Liner. White paper: grey, PE and silicone coated on top side, backprinted with Contra Vision® Performance™ branding and PE coated on the back side.
Liner weight	6.75 oz/yard ² ±0.42 oz/yard ² (160g/m ² ±10g/m ²)
Application temperature	Minimum: 39°F (4°C) air and substrate
Peel adhesion 24 hours	14.4 oz/in (4N/25mm). Printed film on glass, typical value
Peel adhesion 1 month	18 oz/in (5N/25mm). Printed film on glass, typical value
Removability	Minimum 12 months clean removability without adhesive residue at 73°F to 77°F (23°C to 25°C) and RH of 50-60%
Durability	3 years
	Durability stated is for unprinted and untreated material correctly applied to an inert, vertical substrate subject to Mid-European weathering conditions. Some printing inks and drying or curing regimes may reduce the expected lifetime of the printed graphic. Please consult your ink manufacturer for guidance. Incorrect application methods, inadequate window cleaning and preparation and incompatible window treatments may reduce the expected lifetime of the applied material whether printed or unprinted, overlaminated or unlaminated. Mechanically sustained damage, chemical damage and UV-degradation to printed, unprinted, laminated or unlaminated material may also reduce expected durability. Typical application life is eighteen months. All perforated window films are especially vulnerable to damage along the edges and corners, which may lead to premature failure.
Shrinkage	x direction ≤0.6%, y direction ≤0.6% FTM14
Service temp	-13°F to 149°F (-25°C to 65°C)
Shelf life	3 years Under ordinary condition at temperature of 72°F (22°C) and relative humidity of 50-55%
Other info	

Technical Data Sheet



ScorchProtect™ Clear CLPRG502A

Page: 2 of 2
Revision: 1 (CVNA)
Date: 28 June 2023
Author: None

Regulations

Some countries and regions have laws or regulations requiring minimum light passage that may limit or preclude the use of this product on vehicle windows. The user is responsible for determining and complying with all applicable standards.

Substrate Recommendations

This product is not recommended for use on glass with coatings such as anti-reflective, self-cleaning and scratch-resistance, which may be damaged during film removal.

Application Recommendations

Apply the film using a dry application method. Surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination. Final clean with soap and water. Rinse and dry glass after cleaning.

Not to be applied to fresh paint or ink, polycarbonate, rubber, plastic moldings and certain PVCs. In case of doubt, please test prior to final application.

This product is not recommended for use around a sharp angle where there is a limited area either side of the angle.

The film must not touch the rubber window molding. If two graphic panels meet side by side on a window, carefully trim the film so that the panels meet and form a butt seam. Do not overlap the panels.

Observe the minimum application temperature, and the graphics should not be washed within 24 hours of application.

Printing Recommendations

Replacement Liner construction is not recommended for use with UV curing inkjet printers. Depending on the brand of ink and density of the print, "bridging" can occur over the perforated holes after removal of the Replacement Liner, in relatively dark areas of a design. This is eliminated with Universal Liner. We therefore recommend Universal Liner for UV inkjet printing.

After printing the ink must be thoroughly dry, including in the perforated holes in order to avoid any contamination, particularly during lamination.

Environmental

Contra Vision perforated window film is phthalate free and conforms to the latest REACH regulations - please refer to our website for further details.

Contra Vision packaging is produced from recycled cardboard, with polypropylene end bungs and polyethylene wrapping. All of which are fully recyclable, subject to local recycling facilities.

For further information on the environmental benefits of using Contra Vision products and the efforts we're making to improve the sustainability of our material, you can search for "sustainability" on our website.

Contact Information

Contra Vision North America, Inc.
3330 Cumberland Blvd, Suite 500
Atlanta, Georgia 30339
USA

Tel. +1 888 646 5939
Email: technical@contravision.com

This document is intended as a source of information, is given without guarantee, and does not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of the product for their specific intended purpose.

All trademarks in this datasheet are © Contra Vision Ltd